

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended) A magnetic recording medium, comprising:

a substrate; and

a magnetic layer, made of amorphous magnetic material, for magnetically recording information,

wherein the magnetic layer has bumps on a surface thereof, and density of the bumps is not less than $400 \text{ bumps}/\mu\text{m}^2$, and

wherein at least five of the bumps are included in a single magnetic bit.

2. (Original) The magnetic recording medium as set forth in claim 1, wherein the bumps are formed by providing an underlayer, made of nonmagnetic metal element, between the substrate and the magnetic layer.

3. (Original) The magnetic recording medium as set forth in claim 2, wherein the nonmagnetic metal element is aluminum.

4. (Original) The magnetic recording medium as set forth in claim 1, wherein a magnetic compensation temperature thereof is not less than 25°C .

5. (Original) The magnetic recording medium as set forth in claim 1, wherein the magnetic layer is to magnetically record the information by receiving heat and a magnetic field that are applied.

6. (Original) The magnetic recording medium as set forth in claim 2, wherein:
the underlayer has bumps on a surface thereof, and
a compound made of (i) an element constituting the amorphous magnetic material and (ii) the nonmagnetic metal element is formed between the magnetic layer and the underlayer.

7. (Previously presented) A magnetic recording medium, comprising:
a substrate;
a magnetic layer, made of amorphous magnetic material, for magnetically recording information, and
subsequent layers provided on the magnetic layer; wherein
the magnetic layer has bumps on a surface thereof,
height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and
the bumps propagated through to the surfaces of the subsequent layers are provided with a shape different to that of the bumps on the surface of the magnetic layer.

8. (Original) The magnetic recording medium as set forth in claim 7, wherein the bumps are formed by providing an underlayer, made of nonmagnetic metal element, between the substrate and the magnetic layer.

9. (Original) The magnetic recording medium as set forth in claim 8, wherein the nonmagnetic metal element is aluminum.

10. (Original) The magnetic recording medium as set forth in claim 7, wherein a magnetic compensation temperature thereof is not less than 25°C.

11. (Original) The magnetic recording medium as set forth in claim 7, wherein the magnetic layer is to magnetically recording the information by receiving heat and a magnetic field that are applied.

12. (Original) The magnetic recording medium as set forth in claim 8, wherein:
the underlayer has bumps on a surface thereof, and
a compound made of (i) an element constituting the amorphous magnetic material and (ii) the nonmagnetic metal element is formed between the magnetic layer and the underlayer.

13. (Currently amended) A magnetic recording medium, comprising:
a substrate; and
a magnetic layer, made of amorphous magnetic material, for magnetically recording information,
wherein the magnetic recording medium has bumps on a side of the magnetic layer, and density of the bumps is not less than 400 bumps/ μm^2 , and
wherein at least five of the bumps are included in a single magnetic bit.

14. (Original) The magnetic recording medium as set forth in claim 13, wherein the bumps are formed by providing an underlayer, made of nonmagnetic metal element, between the substrate and the magnetic layer.

15. (Original) The magnetic recording medium as set forth in claim 14, wherein the nonmagnetic metal element is aluminum.

16. (Original) The magnetic recording medium as set forth in claim 13, wherein a magnetic compensation temperature thereof is not less than 25°C.

17. (Original) The magnetic recording medium as set forth in claim 13, wherein the magnetic layer is to magnetically recording the information by receiving heat and a magnetic field that are applied.

18. (Original) The magnetic recording medium as set forth in claim 14, wherein:
the underlayer has bumps on a surface thereof, and
a compound made of (i) an element constituting the amorphous magnetic material and (ii)
the nonmagnetic metal element is formed between the magnetic layer and the underlayer.

19. (Previously presented) A magnetic recording medium, comprising:
a substrate;

a magnetic layer, made of amorphous magnetic material, for magnetically recording information, and

subsequent layers provided on the magnetic layer; wherein

the magnetic recording medium has bumps on a side of the magnetic layer, and height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and

the bumps propagated through to the surfaces of the subsequent layers are provided with a shape different than that of the bumps on the surface of the magnetic layer.

20. (Original) The magnetic recording medium as set forth in claim 19, wherein the bumps are formed by providing an underlayer, made of nonmagnetic metal element, between the substrate and the magnetic layer.

21. (Original) The magnetic recording medium as set forth in claim 20, wherein the nonmagnetic metal element is aluminum.

22. (Original) The magnetic recording medium as set forth in claim 19, wherein a magnetic compensation temperature thereof is not less than 25°C.

23. (Original) The magnetic recording medium as set forth in claim 19, wherein the magnetic layer is to magnetically record the information by receiving heat and a magnetic field that are applied.

24. (Original) The magnetic recording medium as set forth in claim 20, wherein:
the underlayer has bumps on a surface thereof, and
a compound made of (i) an element constituting the amorphous magnetic material and (ii)
the nonmagnetic metal element is formed between the magnetic layer and the underlayer.

25. (Currently amended) A magnetic recording device, for causing a magnetic layer of a
magnetic recording medium to magnetically record information, said magnetic recording
medium including: a substrate; and the magnetic layer, made of amorphous magnetic material,
for magnetically recording the information, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic layer has bumps on a surface thereof, and density of the bumps is not less
than 400 bumps/ μm^2 ,

said magnetic recording device comprising magnetic field application means for applying
a magnetic field, which determines a magnetization direction of the magnetic layer, to the
magnetic layer, and

wherein at least five of the bumps are included in a single magnetic bit.

26. (Original) The magnetic recording device as set forth in claim 25, further comprising
heating means for locally heating the magnetic layer, wherein the magnetic field application
means is to apply the magnetic field, which determines the magnetization direction of the
magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic
layer magnetically records the information by receiving heat and a magnetic field that are
applied.

27. (Previously presented) A magnetic recording device, which causes a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; a magnetic layer of amorphous magnetic material, for magnetically recording the information, and subsequent layers provided over the magnetic layer, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic layer has bumps on a surface thereof, and height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and the bumps propagated through to the surfaces of the subsequent layers are provided with a shape different than that on the surface of the magnetic layer,

said magnetic recording device comprising magnetic field application means for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

28. (Original) The magnetic recording device as set forth in claim 27, further comprising heating means for locally heating the magnetic layer, wherein

the magnetic field application means applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

29. (Currently amended) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; and the magnetic layer, made of amorphous magnetic material, for magnetically recording the information, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic recording medium has bumps on a side of the magnetic layer, and density of the bumps is not less than $400 \text{ bumps}/\mu\text{m}^2$, and

wherein at least five of the bumps and/or concaves are included in a single magnetic bit,

said magnetic recording device comprising magnetic field application means for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

30. (Original) The magnetic recording device as set forth in claim 29, further comprising heating means for locally heating the magnetic layer, wherein

the magnetic field application means applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

31. (Previously presented) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; a magnetic layer of amorphous magnetic material, for

magnetically recording the information, and subsequent layers provided on the magnetic layer, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic recording medium has bumps on a side of the magnetic layer, and height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and the bumps propagated through to the surfaces of the subsequent layers are provided with shape different than that of the bumps on the surface of the magnetic layer,

said magnetic recording device comprising magnetic field application means for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

32. (Original) The magnetic recording device as set forth in claim 31, further comprising heating means for locally heating the magnetic layer, wherein the magnetic field application means applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

33. (Currently amended) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; and the magnetic layer, made of amorphous magnetic material, for magnetically recording the information, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic layer has bumps on a surface thereof, and density of the bumps is not less than 400 bumps/ μm^2 , and

wherein at least five of the bumps and/or concaves are included in a single magnetic bit,

said magnetic recording device comprising a magnetic field generator for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

34. (Original) The magnetic recording device as set forth in claim 33, further comprising a heater for locally heating the magnetic layer, wherein the magnetic field generator applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

35. (Previously presented) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; a magnetic layer of amorphous magnetic material, for magnetically recording the information, and subsequent layers provided on the magnetic layer, wherein:

the magnetic layer is made of amorphous magnetic material,

the magnetic layer has bumps on a surface of the magnetic layer, and height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and the bumps propagated through to surfaces of subsequent layers are provided with shape different than that of the bumps on the surface of the magnetic layer,

said magnetic recording device comprising a magnetic field generator for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

36. (Original) The magnetic recording device as set forth in claim 35, further comprising a heater for locally heating the magnetic layer, wherein the magnetic field generator applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

37. (Currently amended) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; and the magnetic layer, made of amorphous magnetic material, for magnetically recording the information, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic recording medium has bumps on a side of the magnetic layer, and density of the bumps is not less than $400 \text{ bumps}/\mu\text{m}^2$, and

wherein at least five of the bumps and/or concaves are included in a single magnetic bit,

said magnetic recording device comprising a magnetic field generator for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

38. (Original) The magnetic recording device as set forth in claim 37, further comprising a heater for locally heating the magnetic layer, wherein the magnetic field generator applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.

39. (Previously presented) A magnetic recording device, for causing a magnetic layer of a magnetic recording medium to magnetically record information, said magnetic recording medium including: a substrate; a magnetic layer of amorphous magnetic material, for magnetically recording the information, and subsequent layers over the magnetic layer, wherein:

the magnetic layer is made of amorphous magnetic material, and

the magnetic recording medium has bumps on a side of the magnetic layer, and height of the bumps on a surface of the magnetic layer is not less than 2% with respect to an average layer thickness of the magnetic layer, and the bumps propagated to surfaces of subsequent layers are provided with shapes different than those of the bumps on the surface of the magnetic layer,

said magnetic recording device comprising a magnetic field generator for applying a magnetic field, which determines a magnetization direction of the magnetic layer, to the magnetic layer.

40. (Original) The magnetic recording device as set forth in claim 39, further comprising a heater for locally heating the magnetic layer, wherein the magnetic field generator applies the magnetic field, which determines the magnetization direction of the magnetic layer, to at least

one part of a heated region in the magnetic layer, so that the magnetic layer magnetically records the information by receiving heat and a magnetic field that are applied.